



Previous Page
Texloc Home Page

FEP Detailed Properties (Fluorinated Ethylene Propylene)

The table below lists a generally accepted summary of properties that we believe to be reliable. Please note that many of these resins are produced in several varieties and property characteristics may vary. Therefore, determination of resin is dependent on the application and this table is only meant to serve as a general guideline.

Properties	ASTM or Unit	FEP
MECHANICAL PROPERTIES		
Specific Gravity	D792	2.15
Elongation %	D638	250~330
Tensile Strength (psi)	D638	2,800~5,000
Flexural Strength (psi)	D790	no break
Compressive Strength	D695	2,200
Tensile Elastic Modulus (Young's Modulus) (psi)	D638	50,000
(psi) Flexural Modulus	D790	78,000~ 92,000
103MPa (103kgf/cm ²)	D790	0.5-0.6 (5.5-6.5)
Flex Life (MIT cycles)	D2176	5,000~ 80,000
Hardness Durometer Shore D	D636	D55
Coefficient of Friction	on steel	0.05
Abrasion Resistance 1000 revs.	Taber	14~20
Impact Strength IZOD 73°F/23°C, notched ft/lbs/in	D256	no break
THERMAL PROPERTIES		
Melting Point	°C (°F)	260 (500)
Upper Service Temperature(20,000h)	°C (°F)	200 (392)
Flame Rating**	UL 94	V-0
Thermal Conductivity	BTU/hr/ft ² /deg F in	1.4
	cal/sec/cm ² , °C/cm	6 x 10 ⁻⁴
Linear Coefficient of Thermal Expansion 10-5 °C	D696	8.3~10.5
Heat of Fusion	BTU/LB	11
Heat of Combustion	BTU/LB	2200
Low Temperature Embrittlement	°C	-268
	(°F)	(-450)
ELECTRICAL PROPERTIES		

Dielectric Constant	D150/103Hz	2.1
	D150/106Hz	2.1
Dielectric Strength 10 mil film	D149	>2000
Volume Resistivity ohm-cm	D257	>10 ¹⁸
Surface Resistivity ohm/sq.	D257	>10 ¹⁷
GENERAL PROPERTIES		
Chemical/Solvent Resistance	D543	Excellent
Water Absorption, 24h	%	<0.01
Deformation Under Load	*D621/100°C	5.0
	**D621/25°C	3.0
Refractive Index		1.338
Limiting Oxygen Index	>95	>95
Properties	ASTM or Unit	FEP

Back to Top

TexLoc, Ltd. Mfg of Precision Fluoroplastic Tubing & Heat Shrink
 4700 Lone Star Blvd. Fort Worth, Texas 76106 U.S.A. Telephone: 817-625-5081
 U.S.A. 800-423-6551 Fax: 817-624-9095 U.S.A. 800-438-9562 Email: texloc@texloc.com

Send mail to jmartin@texloc.com with questions or comments about this web site.
 Last modified: October 25, 2002

* Mylar® and Nomex® are registered trademarks of Dupont Teijin Films.
 Ultem® is registered trademark of GE Polymers. PEEK™ is a registered trademark of Victrex